


BT4102-26



DIVERSIFIED

TESTING LABORATORIES, INC.

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

April 3, 2009

Mr. Diethelm Schussler
A.BERGER GmbH & CO. KG
TEXTILWARENFABRIK
Kuhleshutte
47809 Krefeld
Postfach 10 20 48
47720 Krefeld
Germany

Reference: Laboratory Test Report
Lab Identification No. 9484
Invoice No. 21858 (Attached)

Dear Mr. Schussler:

One (1) fabric sample, identified as **CREASE FREE HEAVY SATIN**, was received and tested in accordance with the National Fire Prevention Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2004 Edition, (Test 1, Small Scale)". The results are as follows:

<u>Specimen Number</u>	<u>Residual Flame (seconds)</u>	<u>Weight Loss (percent)</u>
1	0.0	17.11
2	0.0	18.52
3	0.0	11.07
4	0.0	18.26
5	0.0	18.07
6	0.0	16.51
7	0.0	16.72
8	0.0	16.72
9	0.0	15.39
10	0.0	16.56
AVG.	0.0	16.49

The fabric sample submitted meets the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Karon S. Matkins